



# AALBORG PORTLAND IN WHITE CEMENT

Aalborg Portland, with over 125 year's history, is the global leading player in White Cement with 3.3 million MT capacity and production facilities strategically located in four continents.


More than 70 countries worldwide are served under the global AALBORG WHITE® brand from production plants in Denmark, Egypt, Malaysia, China as well as US , with a reliable supply of consistent quality for all the cement features.

Aalborg Portland supports its partners by providing a consistent and high performance product, value-adding services into the customers' supply chain, extensive technical and customer support, as well as potential cooperation in (co)developing new applications using White Cement.

Aalborg Portland is owned by the Italian Cementir Holding, an international Group with operations in 18 countries, with over 3,000 employees, active in white and grey cement, ready mix concrete, aggregates, concrete products and waste management.

# AALBORG WHITE® PLANTS CAPACITY

TOTAL  
**3.29**  
million t



## AALBORG WHITE® PRODUCTS

- AALBORG WHITE® cement CEM I 52,5 R-SR 5 (made in Denmark)**

Produced in Aalborg, Denmark  
Sold in all European markets as bulk, bigbags and 25kg bags



- AALBORG WHITE® cement CEM I 52,5 R (made in Egypt)**

Produced in Sinai, Egypt  
Currently sold in Benelux, France and Germany as bulk, bigbags and in 25kg bags.



- AALBORG WHITE® cement CEM II/B-LL 42,5 N (made in Egypt)**

Produced in Sinai, Egypt  
Currently sold in Benelux, France and Germany as bulk, bigbags and in 25kg bags.



### AALBORG WHITE® Product Overview

The cement conforms to national/regional standards in the market served	Physical Properties							Chemical Properties				Product Features				
	Strength (MPa)			Initial Setting time	Whiteness	Fineness	SO <sub>3</sub>	Alkalies as Na <sub>2</sub> O	C <sub>3</sub> A	Loss on ignition	High Whiteness	High Strength (28days)	High Early Strength	High Consistency in Quality	Low Alkali Content	Sulphate Resistance
	1 Days	2 Days	28 Days	Mins	Hunter L	m <sup>2</sup> /kg	%	%	%						(SR5-EN 197-1)	
AALBORG WHITE® Product - Product Data Sheet Source: Cementir White Cement Plants																
AALBORG WHITE® cement CEM I 52,5 R - SR 5	Made in Denmark	24	44	72	135	93	400	2.1	≤ 0.3	5	1.1	●	●	●	●	●
AALBORG WHITE® cement CEM I 52,5 R	Made in Egypt	29	42	67	125	93	460	3.4	0.5	6	3.5	●	●	●	●	●
AALBORG WHITE® cement CEM II/B-LL 42,5 N	Made in Egypt	16	24	48	150	92	550	2.4	0.4	6	13.5	●			●	●









